

### APPLICATIONS

Mould release agents for moulds and patterns on non-porous materials such as resin, metal, varnished wood, pore-sealed plaster. Refer to the 2<sup>nd</sup> page of the data product for preparing surfaces.

<b>827</b>	<p>Multipurpose wax in paste form for low porous supports such as wood, machinable slabs etc... Apply with a rag the necessary coat number of WAX 827 according to the porosity of the support.</p>		
	PACKAGING	1 x 1.00 kg	1 x 4.00 kg
<b>841</b>	<p>Wax in solvent phase for non porous supports. Shake before using. Polishable product. Apply 3 coats with a brush on a clean mold. Polish between each coat. It allows to obtain a shiny surface. It is particularly designed for molding laminates or casting resins until 90°C when a neat surface aspect is required.</p>		
	PACKAGING	1 x 0.7 kg	1 x 7.00 kg
<b>851</b>	<p>Heavy wax in spirit suspension. Shake before using. Apply 2 coats with a brush on a clean mold. This release agent must not be polished. It is particularly designed for casting and low pressure RIM applications up to 100°C as well as urethane elastomers. It is not suited to epoxy laminating resins.</p>		
	PACKAGING	1 x 0.7 kg	1 x 7.00 kg
<b>870</b>	<p>Aerosol in pressurised container. Wax in solvent phase. Spray on a clean mold. Remove excess demoulding agent with a cloth, if necessary. It is designed for casting and low pressure RIM applications up to 100°C. It is not suited to epoxy laminating resins.</p>		
	PACKAGING	Aerosol - 1 x 400 ml	
<b>MS 150</b>	<p>Aerosol in pressurised container contains PTFE Spray at 30 cm from the surface of the clean mold. Multipurpose product. Heat resistant up to 300°C. It is not suited to epoxy laminating resins.</p>		
	PACKAGING	Aerosol - 1 x 400 ml	



# DEMOLDING AGENTS

RELEASE AGENTS  
SURFACE PREPARATION - POROUS MOLDS

## APPLICATIONS

These products are designed for surface preparation of patterns in porous materials such as plaster, wood, etc... after which a demoulding agent is applied.

<b>821</b>	<b>PORE-SEALANT.</b> Apply with a brush or spraygun (3 coats). Thin using 1 or 2 parts by volume of 824 for 1 volume of 821.		
	PACKAGING	1 x 0.85 kg	1 x 4.25 kg
<b>824</b>	<b>THINNER</b> for 821 PORE-SEALANT.		
	PACKAGING	1 x 0.85 kg	1 x 4.25 kg
<b>825</b>	<b>PEEL FILM</b> Apply with a brush or spraygun (1 to 2 coats) and observe a interval of 15 minutes between 2 coats. Can be thinned with acetone.		
	PACKAGING	1 x 0.85 kg	
<b>PLASTILINE</b>	Designed to prepare models; yellow, flexible with a thermal treatment up to 80°C.		
	PACKAGING	30 x 0.35 kg	6 x 0.35 kg

## PRECAUTIONS

Normal health and safety precautions should be observed when handling these products :

- ensure good ventilation
- wear gloves and safety glasses

For further information, please consult the product safety data sheet.

## STORAGE

These products can be stored 1 year in a dry place and in original unopened containers at a temperature between +15°C and +25°C. Caution! Some of these products are VERY FLAMMABLE. For further information please refer to safety data sheets.

## GUARANTEE

The information of our technical data sheet are based on our present knowledge and the result of tests conducted under precise conditions. It is the responsibility of the user to determine the suitability of AXSON products, under their own conditions before commencing with the proposed application. AXSON refuse any guarantee about the compatibility of a product with any particular application. AXSON disclaim all responsibility for damage from any incident which results from the use of these products. The guarantee conditions are regulated by our general sale conditions.