

Key Features

FILLER RZ209/8 mixed into epoxy or polyurethane resins increase thermal conductivity, reduce shrinkage and allow thicker castings. The characteristics of the filler is described as atomised, screened powders, and irregular particle shapes.

- Exotherms, Friction materials,
- Resin fillers and heat sinks, Low-level
- Chemical reagents

Physical Properties

| | |
|-------------------------|-----------------------------|
| Purity | 96% AL min |
| | Cu 1.0% max |
| | Mg 1.0% max |
| | Zn 1.0% max |
| Particle Size | < 75 µm |
| Apparent Density | Within range from 0.9 – 1.4 |

Packaging

| |
|--------------|
| PACKS |
| 1 KG |
| 3 KG |
| 5 KG |
| 10 KG |

Disclaimer

Any information, data, advice or recommendation's for processing materials or products supplied by AMT Composites is given in good faith. It remains at all time the responsibility of the customer to ensure that the products and materials recommended are suitable for the production method used, and purpose intended.

Copyright

All rights reserved, including intellectual property rights. Changes to technical data reserved. Delivery subject to availability. Any liability that the data and illustrations are complete, actual or correct is excluded. Designations may be trademarks and/or copyrights of the respective manufacturer, the use of which by third parties for their own purposes may infringe the rights of such owner.
©2018 AMT Composites