

Technical Information

NCS POOLCOAT 73 P1075 PA

NDS1405/847REV1

DURABLE WHITE HIGH PERFORMANCE SURFACE COAT FOR SWIMMING POOL APPLICATIONS WINTER VERSION

DESCRIPTION

NCS POOLCOAT 73 P1075 PA is a Durable White pre-accelerated, thixotropic unsaturated polyester surface coat based on Isophthalic Acid and Neopentyl Glycol designed for use as a protective, decorative layer directly onto the glass reinforced laminate layers in the relining and repair of swimming pools.

FEATURES	BENEFITS
Thixotropic	Minimal drainage with excellent levelling properties
Pre-accelerated	Requires only the addition of suitable catalyst
Fast-curing	Tack-free finish in less than one hour
High gloss	Attractive smooth protective surface
UV-stabilised	Improved weather resistance
Low water absorption	Excellent water resistance
Pre-pigmented	High opacity white shade

OTHER VERSIONS

NCS POOLCOAT 73 P3038 PA	Iso/NPG Pool Blue Poolcoat
NCS POOLCOAT 73 NAT PA	Iso/NPG Clear Poolcoat

TYPICAL LIQUID PROPERTIES

PROPERTY	SPECIFICATION	NCS TEST METHOD
Viscosity @ 25°C, mPa.s	30 000 - 45 000	5.3
Geltime @ 25°C, 2 phs* BUTANOX M50, minutes	6 -14	8
Tack-free time @ 35°C, 2 phs* BUTANOX M50, minutes	60 maximum	25B
Stability in the dark @ 25°C, months	6 minimum	4.1
*phs - parts per hundred surface coat		

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute any other warranty expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials, and in no event shall we be liable for special, incidental, or consequential damages. Our standard conditions of contract will apply to all sales

CURING CHARACTERISTICS

NCS POOLCOAT 73 P1075 PA is pre-accelerated, needing only the addition of catalyst to start the curing reaction.

It should be noted that the addition of monomers, fillers and/or pigments may affect the geltime, cure characteristics and tack-free time of this product.

NCS POOLCOAT 73 P1075 PA is thermosetting and therefore should not be processed at temperatures below 15°C. The Poolcoat should also not be applied if the air temperature is above 32°C and the pool surface temperature is greater than 45°C.

It is essential to thoroughly mix the catalyst into the surface coat.

The minimum recommended catalyst addition is one part per hundred surface coat.

The ambient temperature and the amount of catalyst control the geltime of the gelcoat. In colder temperatures, Butanox M60 is recommended.

APPLICATION

NCS POOLCOAT 73 P1075 PA is formulated to be applied by brush application. The thixotropy has been optimised so that it does not drain when applied to a vertical surface.

Any alteration of the product could result in the poolcoat not performing satisfactorily.

During and immediately after application of NCS POOLCOAT 73 P1075 PA, the work area must be free of moisture and contamination. It is recommended that a swimming pool coated with NCS POOLCOAT 73 P1075 PA should be allowed to stand empty for 5 to 6 days in hot weather and 7 to 10 days in cool weather.

NCS POOLCOAT 73 P1075 PA E must not be considered as a paint, nor must it be applied independently without the prior use of suitable glass reinforcements.

Effect of Temperature

NCS Poolcoat should not be applied onto a surface whose temperature is above 45°C. This is equivalent to an air temperature of 32°C in direct sunlight. The surface will remain slightly tacky and will go white when the pool is filled with water.

For further details refer to NCS Resins 'Suggestions for Lining Swimming Pools with Glass Reinforced Polyester Resins' reference APP030/0.

PIGMENTS & FILLERS

The addition of fillers, solvents or thixotropic additives may downgrade the product and is not generally recommended.

It is recommended that, where mouldings are produced as sub-components of larger structures, or are simply large structures, that sufficient resin and pigment paste are mixed to enable the entire job to be completed, thus ensuring an exact colour match. Similarly, if coloured gelcoat is used, it is recommended that the same batch of material is used throughout the application as well as for sub-components. Thorough stirring of the mix shortly before use is recommended to ensure that the pigment is fully dispersed and that no separation has occurred. Care must be taken not to introduce air into the system. Users are reminded that the final colour of the cured gelcoat and laminate can be affected by the curing system or the colour of the gelcoat or which the pigment paste is added, particularly when heavily filled systems are used, and therefore the colour samples here are intended purely for guidance and exact matching to the final laminate colour cannot be guaranteed. Users are advised to consult application bulletins which deal with the methods of use and scope of application of NCS Resins pigment pastes.

**STORAGE
AND
HANDLING**

To ensure maximum stability and maintain optimum properties, surface coat should be stored in closed containers, maintained below 25°C and away from heat sources and sunlight. All storage should conform to local fire and building codes. Drum stock should be kept to a reasonable minimum with first-in, first-out stock rotation.

Where bung-in-head containers are stored outside, it is recommended that these be stored in a horizontal position to avoid the ingress of water.

**STANDARD
PACKAGE**

Non-returnable metal drums.

**MATERIAL SAFETY
DATA SHEET**

A Material Safety Data Sheet is available from your NCS Resins' representative. Make certain that you obtain a copy of this guide to the safe handling of unsaturated polyester resins and resin systems.

**PLEASE READ AND UNDERSTAND THE MATERIAL SAFETY
DATA SHEET BEFORE WORKING WITH THIS PRODUCT**

WARNING: CARE MUST BE TAKEN TO AVOID DIRECT MIXING OF ANY ORGANIC PEROXIDE (CATALYST) WITH METAL SOAPS, AMINE OR ANY OTHER POLYMERISATION ACCELERATOR OR PROMOTER, AS VIOLENT DECOMPOSITION WILL RESULT!

NCS RESINS BRANCHES AT:

JOHANNESBURG • DURBAN • CAPE TOWN • PRETORIA • PORT ELIZABETH • EAST LONDON